

PA 6G + MOS₂ (POLYAMIDE)

MATERIAL DATA SHEET

- High mechanical strength, stiffness, hardness and toughness
- Good fatigue resistance
- High mechanical damping ability
- Good sliding properties
- Excellent wear resistance
- Good electrical insulating properties
- Good resistance to high energy radiation (gamma- and X-rays)
- Good machinability

PA6G+MOS₂ contains finely divided particles of molybdenum disulphide to enhance its bearing and wear behaviour without impairing the impact and fatigue resistance inherent to unmodified cast nylon grades. It is a very commonly used grade for gears, bearings, sprockets and sheaves.

PROPERTIES	Test methods	Units	VALUES
Colour	-	-	Grey-black
Density	ISO 1183-1	g/cm ³	1.16
Water absorption:			
- after 24/96 h immersion in water of 23°C	ISO 62	mg	52/98
	ISO 62	%	0.76/1.43
- at saturation in air of 23°C / 50% RH	-	%	2.4
- at saturation in water of 23°C	-	%	6.7
Thermal Properties			
Melting temperature (DSC, 10°C/min)	ISO 11357-1/-3	°C	215
Thermal conductivity at 23°C	-	W/(K.m)	0.30
Coefficient of linear thermal expansion:			
- average value between 23 and 60°C	-	m/(m.K)	80x 10 ⁻⁶
- average value between 23 and 100°C	-	m/(m.K)	90x 10 ⁻⁶
Temperature of deflection under load:			
- method A: 1.8 MPa	+ ISO 75-1/-2	°C	80
Max. allowable service temperature in air:			
- for short periods	-	°C	170
- continuously : for 5000 /20000 h	-	°C	105/90
Min. service temperature	-	°C	-30
Flammability:			
- "Oxygen Index"	ISO 4589-1/-2	%	25
- according to UL 94 (1.5 / 3 mm thickness)	-	-	HB / HB
Mechanical Properties at 23°C			
Tension test:			
- tensile stress at yield/ tensile stress at break	+ ISO 527-1/-2	MPa	80/-
	++ ISO 527-1/-2	MPa	50/-
- tensile strength	+ ISO 527-1/-2	MPa	82
- tensile strain at yield	+ ISO 527-1/-2	%	5
- tensile strain at break	ISO 527-1/-2	%	25
	++ ISO 527-1/-2	%	>50
- tensile modulus of elasticity	+ ISO 527-1/-2	MPa	3400
	++ ISO 527-1/-2	MPa	1650
Compression test			
- compressive stress at 1/2/5 % nominal strain	ISO 604	MPa	25 / 49 / 88
Creep test in tension to produce 1% strain in 1000 h ($\dot{\epsilon}$ 1/1000)			
	+ ISO 899-1	MPa	21
	++ ISO 899-1	MPa	9
Charpy impact strength - Unnotched	ISO 179/1eU	kJ/m ²	No break
Charpy impact strength - Notched	ISO 179/1eA	kJ/m ²	3.5
Izod impact strength - Notched	+ ISO 180/A	kJ/m ²	3.5
	++ ISO 180/A	kJ/m ²	7
Ball indentation hardness	ISO 2039-1	N/mm ²	160
Rockwell hardness	ISO 2039-2	-	M84

Electrical Properties at 23 °C				
Electric strength	+	IEC 60243-1	kV/mm	22
	++	IEC 60243-1	kV/mm	16
Volume resistivity	+	IEC 60093	Ohm.cm	>10 ¹⁴
	++			>10 ¹²
Surface resistivity	+	IEC 60093	Ohm	>10 ¹³
	++	IEC 60093	Ohm	>10 ¹²
Relative permittivity ϵ_r : - at 100 Hz	+	IEC 60250	-	3.6
	++	IEC 60250	-	6.6
- at 1 MHz	+	IEC 60250	-	3.2
		IEC 60250	-	3.7
Dielectric dissipation factor $\tan \delta$: - at 100 Hz	+	IEC 60250	-	0.012
	++	IEC 60250	-	0.14
- at 1 MHz	+	IEC 60250	-	0.016
	++	IEC 60250	-	0.05
Comparative tracking index	+	IEC 60112	-	600
	++	IEC 60112	-	600

Note: 1 g/cm³ = 1,000 kg/m³ ; 1 MPa = 1 N/mm² ; 1 kV/mm = 1 MV/m.

+ values referring to dry material

++ values referring to material in equilibrium with the standard atmosphere 23°C / 50% RH (mostly derived from literature)

The information contained in this technical data sheet cannot be construed as a promise or guarantee of specific properties of our products. Any determination of the suitability of a particular material and part design for any use contemplated by the user is the sole responsibility of the user. The information contained in this technical data sheet is based on present knowledge and may be subject to change without further notice.